


Product Data Sheet



Welsh Blue Pennant

Description

Appearance	Fine Grain Carboniferous Sandstone
Finishes	Sawn, Flamed, Fine Picked and Cropped
Governing Standards	Where applicable BS EN 1343 : 2001 will be applied.
Quarry of Origin	Neath, South Wales

Physical Properties

Work Dimensions	To customers specification
Tolerances on Dimensions	Class 2
Compressive Strength	175 Mpa
Flexural Strength	22 MPa
Material Density	2550 kg/m ³ (typically)
Slip Resistance	74 Wet – TLR Slider Test 73 Dry – TLR Slider Test
Freeze Thaw	Passed
Water Absorption	0.80 %

Supply

Crate Size	Maximum 1.8 tonnes. Approx size 1.0 x 1.0 x 0.80 high
Packaging	Wooden Pallets suitable for transportation by fork lift.

Cleaning and Maintenance

Use of mechanical cleaning, especially wire brushing, should be avoided as this will reduce, over time, skid resistance. Washing with clean water should be adequate but not pressure jetting as this could eventually remove the jointing material